


Fibreglass (GRP) Kit

Ideal for Lining, Coating & Repairing Fibreglass

Product Overview

A fibreglass membrane designed to protect, repair and restore timber surfaces, extending their operational lifetimes.

Ideal for: timber surfaces such as roofing structures, architectural surfaces, building components and other fibreglass structures exposed to water.



Resin Library
SUPPLIES

Benefits



Fast Cure Times

Partial cures within 1 hour



Water Resistant

Seamless surfaces provide resistance to water and other substances across its lifetime



Ease of Installation

Each kit comes with materials and tools with a range of detailed guides available.



Excellent Bonding

Fibreglass, with a primer, forms a strong unified bond with existing fibreglass.



Strong & Durable

Each kit comes with materials and tools with a range of detailed guides available.



Chemical Resistance

Demonstrates broad chemical resistance to selected chemicals

Application Characteristics

Installed via hand-layup, this fibreglass kit is designed to create seamless linings, coatings and repairs to timber structures, presenting excellent adhesion, contouring to the main surface and providing a high strength-to-weight ratio that can also be enhanced with added layers.

Reaching a partial cure in as little as an hour, the laminate can be abraded, making it consistent with the underlying surface. Thereafter, a protective topcoat/flowcoat can be applied for both added protection, waterproofing and aesthetic purposes.

System Design

MATERIALS		SPECIFICATION
FIBREGLASS LAMINATE	POLYESTER RESIN	1.5 - 1.7 kg/m ²
	GLASS FIBRE MATTING	600 gram CSM (single layer)

Note: coverage levels will vary with surface profile and temperature

WARNING! Read the Safety Data Sheets (SDSs) available for download on the product page. Wear appropriate protective eyewear, clothing, and gloves and other PPE. Perform a full risk assessment, method statement and COSHH form in advance.

Fibreglass (GRP) Kit

Ideal for Lining, Coating & Repairing Fibreglass

Laminate Mechanical Properties

PROPERTY	VALUE	STANDARD*
THICKNESS	1.20 +/- 0.15 mm	-
SHORE D HARDNESS	86.2 +/- 1.4	ISO 868
DENSITY	1.44 +/- 0.01 kg/m ³	ISO1183-1
WEIGHT/AREA	1.9 +/- 0.1 kg/m ²	-
TENSILE STRENGTH	81.9 +/- 8.5 MPa	ASTM D3039
TENSILE MODULUS	6552 +/- 819 MPa	
FLEXURAL STRENGTH	183.6 +/- 26.8 MPa	ASTM D7264
FLEXURAL MODULUS	5364 +/- 507 MPA	

*Data based on third-party, independent testing

Surface Design

Suitable for interior, vertical and overhead repairs and refurbishments of existing fibreglass structures, such as:

- Corners and edges & vertical surfaces
- Interior and exterior surfaces
- Surfaces housing water*
- Surface containing chemicals**
- Overhead surfaces***

requires suitable topcoat/flowcoat resin to be applied for full protection; **requires chemically resistant flowcoat/topcoat *a solid platform should be in place to support*

Designed as a protective lining and coating system for timber surfaces as part of a patch repair, refurbishment or as a pre-emptive protective layer.

Substrate Requirements

The base timber surface should be free from dust, debris, grease and other contaminants. OSB3 timber is recommended as this does not require preparation. More invasive surface preparation may be required if an existing membrane is on the surface. The substrate should be dry to 75% RH as per BS8204 and should have no rising damp and ground water pressure.

Installation Guidance

Apply within a temperature range of 10 – 25 °C and a maximum air humidity of 85%.

Apply the system and ensure the repair does not move prior to curing (see Curing Times table).

Do not create layers exceeding 4 mm (approx. 3 layers of laminate) without allowing time to cure; exotherms can form and lead to shrinkage.

Catalyse a workable amount of polyester resin and apply a thin layer to the fibreglass surface. Place dry or pre-wetted matting onto the damaged area. Saturate with resin and then consolidate using a paddle roller. Allow to cure in accordance with cure adjacent times.

Topcoat application: confirm with manufacturer of paint before using.

Please follow user manual available on the Downloads section of the product page.

Limitations

- Not intended as a substitute for structural repair.
- Do not apply to damp fibreglass or equivalent

Example Applications

Suitable for the repair, refurbishment and pre-emptive protection of timber surfaces.

Fibreglass (GRP)

Ideal for Lining, Coating & Repairing Fibreglass

Performance Considerations

With the aid of a resin primer, fibreglass is able to bond seamlessly to existing fibreglass, acting as a protective shield. Coupled with the superior mechanical and waterproofing properties of the system, users can expect a more durable surface in the form of a new installation, upgrade or repair.

This ultimately means a reduction in the need for future repairs, maintenance and cleaning and an overall extended lifetime. An aesthetic finish can be created with the inclusion of an added topcoat/flowcoat or a compatible paint system.

Environmental and health considerations are controlled during the manufacture and storage of the products by Resin Library. The performance of this product is dependent on the skill of the user.

Ordering

Resin Library Fibreglass Repair Kits for Fibreglass are available online via

www.resinlibrary.com/product/fibreglass-grp-repair-kit/



Kit Sizes

	FIBREGLASS REPAIR KITS						
SIZE (m ²)	0.1	0.25	0.5	1	2	3	5

Cure Times

	10°C	20°C
PARTIAL CURE	4 hours	1 hour
FULL CURE	48 hours	24 hours

Storage

	RECOMMENDATIONS
SHELF LIFE	6 months from date of receipt in original, unopened containers
STORAGE CONDITIONS	Store in a cool, dark and dry environment Keep away from sources of ignition and contamination. Store in original sealed container at temperatures under 20 °C. Protect from direct sunlight.

Tool Cleaning

Tools should be soaked in acetone prior to curing to prevent resin hardening in between usage. Resin hardening occurs after 20 minutes.

Note

No resin system is completely resistant to changes in colour over time. Colour changes in polyester resin topcoat are dependent on UV exposure, temperatures and duration of water exposure. Such changes can be offset by the addition of a suitable topcoat.

Disclaimer

This document is for general information purposes only. It does not constitute advice. Resin Library is not liable for any outcomes. The use of information linked to this document is at the user's own risk. The content of this document is not intended to be a substitute for professional advice. Users should not disregard in obtaining professional advice.

Contact Us

WEB: www.resinlibrary.com/contact-us

EMAIL: sales@resinlibrary.com

TEL: 029 21 900 282